



Application Guide

BLOCKSIL CUT EDGE PRIMER

Cut edge primer converts rust and gives a +20 year corrosion resistance on metals

Surface Preparation:

Loose rust and paint has to be brushed off the surface. Do not apply to wet surfaces or ice.

Application:

The one-part system is applied directly to the rusty surface. *Two coats – 1st coat, blue, 2nd coat, silver. All rusted areas must be coated.*

Supplied in 5 litre tins (5 litres Silver & 5 litres Blue)

Method:

Applied by brush, dries quickly, so both coats can be done in the one day.

Clean up Considerations:

All equipment should be cleaned immediately after use with Thinner No. 1.

It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied.

Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

Coverage:

2 Litres (1 blue coating & 1 silver coating covers 15 square metres or 70 linear metres)

Exposure controls / personal protection

Precautions

All PPE, including RP, used to control exposure to hazardous substances must be selected to meet the requirements of the COSHH regulations. Gloves, Safety glasses in case of splashes.

Storage

Store between 5 & 25°C in a well-ventilated, dry place, away from sources of heat, ignition and direct sunlight. Protect from frost. Prevent unauthorized opening of containers they should be properly resealed and kept upright. Store separately from oxidising agents and any strong alkaline or acidic materials.

Shelf life

Approximately 12 months on un-opened container.

Marking

HAZARD symbols:



Always refer to Safety Data Sheet before use